




Mapefill

High-flow non-shrink cementitious anchoring grout



WHERE TO USE

For precision anchoring of machinery and metallic structures.

Some application examples

- Anchoring machine tools by casting below the machine base.
- Anchorage structural steel work.
- Filling rigid joints between elements in concrete and precast concrete structures.
- Installations below wall level, etc.

TECHNICAL CHARACTERISTICS

Mapefill is a pre-blended powdered grout composed of high strength cement, graded aggregates and special additives with an expansive agent formulated by the MAPEI research laboratories.

Mapefill when mixed with water is transformed into a fluid grout without segregation that is able to fill intricate spaces.

Mapefill, due to its expansive agent, is characterized by a total absence of shrinkage in its plastic phase (ASTM norm 827) and its hardened phase (UNI norm 8147) and develops very high early flexural and compressive strength.

Mapefill also has the following qualities:

- excellent impermeability to water;
- excellent adhesion to iron and concrete;

- excellent resistance to dynamic/mechanical stress;
- modulus of elasticity and thermal expansion coefficient similar to those of high quality concrete;
- **Mapefill** does not contain metal aggregates or aluminium dust.

Mapefill meets all the main requirements for EN 1504-9 (*"Products and systems for the protection and repair of concrete structures; definitions, requirements, quality control and conformity assessment. General principles for the use of products and systems"*) and the minimum requirements for EN 1504-6 (*"Anchoring steel reinforcement"*).

RECOMMENDATIONS

- Do not use **Mapefill** for structural repair by pouring in forms (use **Mapegrout Hi-Flow**).
- Do not use **Mapefill** for vertical applications by spray or trowel (use **Mapegrout Thixotropic**).
- Do not add cement or additives to **Mapefill**.
- Do not add water when the mix has started to set.
- Do not use **Mapefill** if the bag is damaged or has already been opened.
- Do not apply **Mapefill** at temperatures below +5°C.

APPLICATION PROCEDURE

Preparing the substrate

- Remove all deteriorated concrete down to sound substrate.

Mapefill



Repairing rigid joints of a highway bridge with Mapefill

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

Type:	CC
Consistency:	powder
Colour:	grey
Maximum aggregate size (mm):	2.5
Bulk density (kg/m ³):	1,300
Dry solids content (%):	100
Chloride ions content: - minimum requirements ≤ 0.05% - according to EN 1015-17 (%):	≤ 0.05

APPLICATION DATA (at +20°C - 50% R.H.)

Colour of mix:	grey
Mixing ratio:	100 parts of Mapefill with 14-15 parts water (approx. 3.50-3.75 l per 25 kg bag)
Slip value of mortar according to EN 13395-2 (cm):	> 45
Density of mix (kg/m ³):	2,250
pH of mix:	> 12.5
Application temperature range:	from +5°C to +35°C
Pot life of mix:	approx. 1 h

FINAL PERFORMANCE (14.5% blending water)

Performance characteristic	Test method	Requirements according to EN 1504-6	Product performance
Compressive strength (MPa):	EN 12190	> 80% of the value declared by the manufacturer	30 (after 1 day) 55 (after 7 days) 70 (after 28 days)
Flexural strength (MPa):	EN 196/1	not required	5 (after 1 day) 8 (after 7 days) 9 (after 28 days)
Modulus of elasticity in compression (GPa):	EN 13412	not required	27 (after 28 days)
Bond strength to concrete (MC 0.40 type substrate - water/cement ratio = 0.40) according to EN 1766 (MPa):	EN 1542	not required	≥ 2 (after 28 days)
Impermeability to water - penetration depth - (mm):	EN 12390/8	not required	< 5
Free expansion in the plastic phase (%):	ASTM 827	not required	≥ 0.3
Drawing resistance of the steel rods - movement under a 75 kN load (mm):	EN 1881	≤ 0.6	< 0.6
Adherence tension of rods anchored with Mapefill (MPa):	EN 1881 (*)	not required	> 25
Reaction to fire:	EN 13501-1	Euroclass	A1, A1 _{fl}

(*) Sample made according to EN 1881 standards, assuming uniform stress distribution between the reinforcing rods and Mapefill

- Scarify the surface and completely eliminate dust, oils, grease, debris and laitance.
- Soak the sides of the cavity to be filled with water. Before pouring, wait for the excess water to evaporate. To facilitate the elimination of unabsorbed water, use compressed air and a sponge if necessary.

Preparing the grout

Pour into a concrete mixer 3.50-3.75 litres of water. Start concrete mixer and slowly add **Mapecoll** continuously. Mix for 1-2 min., remove from the sides of the concrete mixer any powder that is not well blended; remix for another 2-3 minutes until a fluid homogeneous paste is obtained. According to the quantities to be prepared, a grout mixer or a mechanical mixer can be used paying careful attention to avoid the formation of air bubbles. Mixing by hand is not recommended.

Application

Pour **Mapecoll** from one side only in a continual flow encouraging the discharge of air bubbles into the appropriate area which should not be less than twice the diameter of the bar to be anchored. The use of **Mapecoll** for connecting precast concrete elements and the filling of rigid joints is recommended for thicknesses up to 60 mm. It is not necessary to vibrate the grout mechanically; to facilitate the filling of spaces that are particularly difficult, use a wood list or an iron rod.

Addition of fine gravel

For filling cavities that have dimensions greater than those indicated, add **Gravel 6-10** not exceeding 30% by weight of **Mapecoll**. Because certain characteristics may vary, such as workability and strength, it is advisable to carry out preliminary tests at the work site or to consult our Technical Services Department.

INSTRUCTIONS TO BE OBSERVED BEFORE AND AFTER APPLICATION

- At temperatures around +20°C, no particular precautions are required.
- In hot weather it is advisable not to expose the material to sun and to use cold water in preparing the mix.
- In low temperatures it is advisable to use water that is at +20°C.
- After casting, **Mapecoll** must be properly cured; the surface of grout exposed to the air must be protected from rapid water evaporation that can cause the formation of surface cracks due to plastic shrinkage especially in hot and/or windy weather.
- Spray water on surface exposed to air the first 24 hours of curing or apply an anti-evaporant.

Cleaning

Fresh grout can be removed from tools with water. After curing, cleaning becomes very difficult and can only be done mechanically.

CONSUMPTION

1.95 kg/dm³ of cavity to be filled.

PACKAGING

25 kg bags.

STORAGE

Mapecoll may be stored for up to 12 months in its original packaging. The product complies with the conditions of Annex XVII to Regulation (EC) N° 1907/2006 (REACH), item 47. The product is available in special 25 kg vacuum-packed polyethylene bags which may be stored outside for the entire construction phase of the site. Rain has no effect on its characteristics.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Mapecoll is irritant, it contains cement that when in contact with sweat or other body fluids causes irritant alkaline reaction and allergic reactions to those predisposed. It can cause damage to eyes. In case of contact with eyes or skin wash immediately with plenty of water and seek medical attention. It is recommended to use protective gloves and goggles. For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

All relevant references for the product are available upon request and from www.mapei.com



Anchoring of structural steel work with Mapecoll



Flow test recording to UNI 13395-2



Determination of retained expansion according to UNI 8147

Mapefill



BUILDING THE FUTURE

305-10-2013

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

(GB) A.G. BETA